



1205 ELASTOMERIC, SMOOTH, KNIFE/TROWEL GRADE, CAULK & SEALANT

DESCRIPTION

Anvil Elastomeric, Smooth, Knife / Trowel Grade Caulk & Sealant is a heavy bodied, flexible, siliconized elastomeric caulk and sealant for filling and patching cracks and voids on masonry, stucco, concrete, wood, metal, brick, stone, marble, and glass prior to applying finish. Excellent for cracks, joints, openings around doors, windows, siding panels, entry pipes, vents, flashing, steps, and chimneys. *Anvil Elastomeric, Smooth, Knife/Trowel Grade Caulk & Sealant* provides excellent adhesion, long life, and is resistant to failure by expansion, contraction, or other joint movement. Fast drying and may be painted with latex or oil base paints. For use on interior or exterior surfaces.

SURFACE PREPARATION

Apply to clean, dry, grease-free surfaces. Joint dimensions not to exceed 1/4" x 1/2" deep. Use polyethylene backing rod for depths exceeding 1/2", especially after routing out masonry joints to remove weakened material.

APPLICATION

Use broad knife or trowel.

LIMITATION OF LIABILITY

This product is manufactured to rigid control specifications. It is impossible to control the use and application. Therefore, the manufacturers sole liability is limited to replacing quantities of product proven to be defective. The manufacturer disclaims any liability for the cost of labor to repaint or any other use of the product.

Page 1 of 1

TECHNICAL DATA

PRODUCT NUMBER: 1205

RESIN: Acrylic Latex

COLOR: White

GLOSS: Flat

SOLID CONTENT:
BY WEIGHT: 81.97%
BY VOLUME: 70.85%

RECOMMENDED COVERAGE:
25 Sq. Ft./Gal.

% PIGMENT BY WEIGHT: 55.8

% VEHICLE BY WEIGHT: 44.2

VISCOSITY: Mastic-like

WEIGHT PER GALLON: 13.5 lbs

FLASH POINT: N/A

DRYING TIME: 70 F 50% R.H
Touch - 1/2 hour
Paint over - 1 to 2 hours
Full cure - 72 hours

Do not apply when rain, cold or nightfall is imminent. do not apply below 50 F. Drying and cure time are influenced by ambient temperature and relative humidity.

THINNER/CLEANUP: Water

TINTING: Not Applicable

AVAILABLE IN QTS, 1 & 5 GALLON PAILS

VOC: 46.2 grams/liter

Revised 1-09 Supersedes all prior publications GRO

