



# 1214 ELASTOMERIC, TEXTURED KNIFE/ TROWEL GRADE, CAULK & SEALANT

## DESCRIPTION

**Anvil #1214 Elastomeric, Textured Knife / Trowel Grade Caulk & Sealant** is a heavy bodied, flexible, elastomeric caulk and sealant for filling and patching cracks and voids on vertical masonry, stucco, and concrete block. **Anvil #1214 Elastomeric, Textured, Knife/Trowel Grade Caulk & Sealant** provides excellent adhesion, long life, and is resistant to failure by expansion, contraction, or other joint movement. Fast drying and may be painted with latex or oil base paints. For use on interior or exterior surfaces.

## SURFACE PREPARATION

Surface must be free of dirt, oil, grease, efflorescence, chalk, mildew, and loose material. Any residual chalk left after pressure washing should be sealed with **Anvil #230 or #231 Chalky surface conditioner**. Joint dimensions not to exceed 1/4" x 1/2" deep. Use polyethylene backing rod for depths exceeding 1/2", especially after routing out masonry joints to remove weakened material.

## APPLICATION

Use broad knife or trowel.

## LIMITATION OF LIABILITY

This product is manufactured to rigid control specifications. It is impossible to control the use and application. Therefore, the manufacturers sole liability is limited to replacing quantities of product proven to be defective. The manufacturer disclaims any liability for the cost of labor to repaint or any other use of the product.

Page 1 of 1

## TECHNICAL DATA

**PRODUCT NUMBER:** 1214 Elastomeric Textured Knife/Trowel Grade Caulk & Sealant

**RESIN:** Acrylic Latex

**COLOR:** White

**GLOSS:** Flat

**SOLID CONTENT:**  
BY WEIGHT: 79.4%  
BY VOLUME: 70.2%

**RECOMMENDED COVERAGE:**  
10 to 20 Sq. Ft./Gal.

**% PIGMENT BY WEIGHT:** 52.2%  
**% VEHICLE BY WEIGHT:** 27.2%

**VISCOSITY:** Mastic-like

**WEIGHT PER GALLON:** 11.95 lbs

**FLASH POINT:** N/A

**DRYING TIME:** 70 F 50% R.H.  
Touch - 1 hour  
Paint over - 2 to 4 hours  
Full cure - 1/8" thick single coat - 72 hours

Do not apply when rain, cold or nightfall is imminent. do not apply below 50 F. Drying and cure time are influenced by ambient temperature and relative humidity.

**THINNER/CLEANUP:** Water

**TINTING:** Not Applicable  
**AVAILABLE IN QUARTS AND GALLONS**  
**VOC:** 46.4 grams/liter

Revised 1-09 Supersedes all prior publications GRO

